



ALPHA 1 (ESR)

Forged High Speed Steel

Chemical composition

	С	Cr	Мо	W	Со	V
ALPHA1	0.8	4.0	8.5	1.7	-	1.2
ALPHA2	0.9	4.2	5.0	6.5	-	1.9
ALPHA3	1.2	4.1	5.0	6.2	-	3.0
ALPHA4	1.3	4.2	4.5	5.5	-	4.0
ALPHA7	1.0	4.0	8.6	1.8	-	1.9

Standards; AISI M1. Werkstoff 1.3346.

Properties

	Hardness HRC	
ALPHA1	≤ 65	
ALPHA2	≤ 64	
ALPHA3	≤ 66	
ALPHA4	≤ 66	
ALPHA7	≤ 66	

ALPHA1	8.0	225
	Density g/cm ³	Young's modulus GPa

Description

Conventional molybdenum based high speed steel manufactured according to Union Electric Åkers specification.

ALPHA1 is also available further refined by ESR (Electro Slag Remelting).

ALPHA1 is supplied in through hardened condition.

Applications

Work rolls in 20-high mills for cold rolling of ferrous and non ferrous products.

Work rolls in Z-high mills for cold rolling of ferrous and non ferrous products.

Smaller diameter 2-high and 4-high narrow strip mill work roll for cold rolling of ferrous and non ferrous products.

Features & Benefits

- ALPHA1 offers a good compromise between toughness and hardness.
- Good grindability.
- High thermal shock resistance.

Comparative properties

	Wear resistance	Toughness	Grindability
ALPHA1			
ALPHA2			
ALPHA3			
ALPHA4			
ALPHA7			

Union Electric Åkers www.uniones.com

These data are indicative and can be changed at any time without prior notice © 2020 Union Electric Steel Corporation