

NARVA8 A (ESR)

Forged Tool Steel

Chemical composition

	C	Cr	Mo	W	Co	V
NARVA8 A	0.6	8.0	1.3	1.1	-	-
NARVA8 B	0.9	8.0	1.5	-	-	2.5

Properties

	Hardness HRC	Young's modulus GPa
NARVA8 A	≤ 61	210
NARVA8 B	≤ 63	222

Comparative properties

	Wear resistance	Toughness	Grindability
NARVA8 A	=====	=====	=====
NARVA8 B	=====	=====	=====
NARVA5 B	=====	=====	=====
NARVA5 A	=====	=====	=====

Description

8% chromium vacuum degassed tool steel manufactured according to Union Electric Åkers specification.

NARVA8 A is normally through hardened but can for some special applications be induction hardened.

NARVA8 A is also available further refined by ESR (Electro Slag Remelting).

Applications

1st Intermediate rolls in 20-high mills for cold rolling of ferrous and non ferrous products.

2nd Intermediate rolls in 20-high mills for cold rolling of ferrous and non ferrous products.

Work rolls in highly stressed 2-high and 4-high narrow strip mills for cold rolling of ferrous and non ferrous products.

Features & Benefits

- NARVA8 A is particularly suitable for more severe applications due to the good resistance to cracks due to rolling incidents, abrasive wear and surface fatigue.
- Good compromise between hardness-toughness in hardness range 56-60 HRC.